

Material Requirements

TAMKO AWAPLAN VERSA-SMOOTH	1 ply
TAMKO TAM-GLASS PREMIUM [®] or TAM-PLY IV [®] Fiberglass Ply Sheet	2 plies
Interply Asphalt (Per 100 sq. ft.)	Approx. 69 lbs.
Flood Coat Asphalt (Per 100 sq. ft.)	Approx. 60 lbs.
Gravel (Per 100 sq. ft.)	Approx. 400 lbs.

Slope: Positive drainage up to 3 in. per linear ft. For slopes above 3/4 in. per linear ft., fastening of the AWAPLAN VERSA-SMOOTH and the roofing felts is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Asphalt: The asphalt should be certified by the manufacturer to meet ASTM D-312, Type III for slopes up to 1/4 in. and Type IV for slopes up to 3 in.

AWAPLAN VERSA-SMOOTH: Starting at the low point of the roof, install 1 ply of TAMKO AWAPLAN VERSA-SMOOTH, side lapped 4 in. and end lapped 6 in. Apply at a right angle to the slope of the roof. The AWAPLAN VERSA-SMOOTH should be solidly adhered to the insulation (pressed into the hot asphalt) with approximately 23 lbs. (±15%) of specification asphalt per 100 sq. ft. The asphalt should be above 400° F at the point of application and mopped no more than 4 ft. in front of the roll.

Alternately, the AWAPLAN VERSA-SMOOTH may be installed by sufficiently heating the back side with a torch at the juncture of the insulation and the AWAPLAN VERSA-SMOOTH roll to form a bead of melted asphalt as the AWAPLAN VERSA-SMOOTH is rolled out. Use care when applying heat as damage can occur to the product by overheating.

Fiberglass Ply Sheet 2 Ply Installation: Over the base ply, install 2 plies of TAM-GLASS PREMIUM or TAM-PLY IV in specification asphalt. Starting from the low point of the roof, apply a 1/2 m width, then a full 1 m width. Follow with full 1 m widths, shingle fashion, lapping each ply 20-11/16 in. in such a manner so that at least 2 plies cover the base ply at any one point. Approximately 23 lbs. (±15%) of specification asphalt per 100 sq. ft. should be used to embed each ply.

Surfacing: Apply a flood coat of 60 lbs. (±15%) of specification asphalt per 100 sq. ft. over the entire surface. While hot, embed approximately 400 lbs. of clean roofing gravel or 300 lbs. of slag per 100 sq. ft. of completed roof area.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements: Contact TAMKO for information on U.L. systems requirements.


CAUTION: The National Institute for Occupational Safety and Health (NIOSH) has concluded that fumes of heated asphalt are a potential occupational carcinogen. Apply heat to these products only when required for proper application and only in a well ventilated area. Avoid breathing the fumes, and avoid skin contact. Do not burn these products.



SPECIFICATION SUBMITTAL

244 AWAPLAN VERSA-SMOOTH

INSULATED DECKS



Material Requirements

TAMKO AWAPLAN VERSA-SMOOTH	1 ply
TAMKO TAM-CAP®	
Fiberglass Mineral Surfaced Cap Sheet	1 ply
Asphalt (Per 100 sq. ft.)	Approx. 46 lbs.

Slope: Positive drainage up to 3 in. per linear ft. For slopes above 3/4 in. per linear ft., fastening of the AWAPLAN VERSA-SMOOTH is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Asphalt: The asphalt should be certified by the manufacturer to meet ASTM D-312, **Type III for slopes up to 1/4 in.** and **Type IV for slopes up to 3 in.**

AWAPLAN VERSA-SMOOTH: Starting at the low point of the roof, install 1 ply of TAMKO AWAPLAN VERSA-SMOOTH, beginning with a 1/2 m width, then a full 1 m width, side lapped 4 in. and end lapped 6 in. Apply at a right angle to the slope of the roof. The AWAPLAN VERSA-SMOOTH should be solidly adhered to the insulation (pressed into the hot asphalt) with approximately 23 lbs. (±15%) of specification asphalt per 100 sq. ft. The asphalt should be above 400°F at the point of application and mopped no more than 4 ft. in front of the roll.

Alternately, the AWAPLAN VERSA-SMOOTH may be installed

by sufficiently heating the back side with a torch at the juncture of the insulation and the AWAPLAN VERSA-SMOOTH roll to form a bead of melted asphalt as the AWAPLAN VERSA-SMOOTH is rolled out. **Use care when applying heat as damage can occur to the product by overheating.**

TAM-CAP Mineral Surfaced Cap Sheet: Starting at the low point of the roof, apply 1 ply of TAMKO TAM-CAP, side lapping each sheet 2 in. and end lapping 6 in. over the preceding sheets. Fully mop each sheet with specification asphalt at the rate of 23 lbs. (±15%) of specification asphalt per 100 sq. ft. On slopes of 1 in. per foot or greater, nail adjacent to top edge on 12 in. centers. **NOTE: Before application of TAM-CAP, cut into 12 ft. to 18 ft. lengths, allow to flatten and relax. Stagger the end laps.**


Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:
Contact TAMKO for information on U.L. systems requirements.

CAUTION: The National Institute for Occupational Safety and Health (NIOSH) has concluded that fumes of heated asphalt are a potential occupational carcinogen. Apply heat to these products only when required for proper application and only in a well ventilated area. Avoid breathing the fumes, and avoid skin contact. Do not burn these products.

For complete information on TAMKO's recommendations and requirements, consult TAMKO's web site at www.tamko.com
TAMKO Building Products, Inc., P. O. Box 1404, Joplin, MO 64802 • 1-800-641-4691 • www.tamko.com

TAMKO® and Tam-Cap® are registered trademarks of TAMKO Building Products, Inc.



Material Requirements

TAMKO AWAPLAN VERSA-SMOOTH	2 plies
Asphalt (Per 100 sq. ft.)	Approx. 46 lbs.
Surfacing (Options Below)	
(1) Flood Coat Asphalt (Per 100 sq. ft.)	Approx. 60 lbs.
Gravel (Per 100 sq. ft.)	Approx. 400 lbs.
(2) Surface Coat: (Per 100 sq. ft.)	
(a) Fibered Aluminum Coating	1-1/2-2 gals.
(b) Emulsion Coating	3 gals.
(c) Asphalt Glaze Coating	20 to 25 lbs.
(d) TAM-GUARD or White Elastomeric Coating	2 gals.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN VERSA-SMOOTH membrane is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Asphalt: The asphalt should be certified by the manufacturer to meet ASTM D-312, **Type III for slopes up to 1/4 in.** and **Type IV for slopes up to 3 in.**

AWAPLAN VERSA-SMOOTH 2-Ply Installation: Over the insulation, install 2 plies of AWAPLAN VERSA-SMOOTH in specification asphalt. Starting at the low point of the roof, apply the first ply of AWAPLAN VERSA-SMOOTH beginning with a 1/2 m. width, then a full 1 m. width, side lapped 4 in. and end lapped 6 in. Start the second ply of AWAPLAN VERSA-SMOOTH

beginning with a full 1 m. width, side lapped 4 in. and end lapped 6 in. Apply at a right angle to the slope of the roof. The AWAPLAN VERSA-SMOOTH should be solidly adhered to the insulation or previous ply (pressed into the hot asphalt) with approximately 23 lbs. (±15%) of specification asphalt per 100 sq. ft. The asphalt should be above 400° F at the point of application and mopped no more than 4 ft. in front of the roll.

Surfacing: Select one of the following surfacings:

- (1) **Flood Coat and Gravel:** Apply a flood coat of 60 lb. (±15%) of specification asphalt per 100 sq. ft. over the entire surface. While hot, embed approximately 400 lb. of clean roofing gravel or 300 lb. of slag per 100 sq. ft. of completed roof area, or
- (2) **Surface Coat:** Coat the entire roof surface with (a) Fibered Aluminum Roof Coating at a rate of 1-1/2 to 2 gal. per 100 sq. ft. or (b) Emulsion Roof Coating at a rate of not less than 3 gals. per 100 sq. ft., or (c) a surface grade hot asphalt using a min. of 20 lbs. and a max of 25 lbs. per 100 sq. ft., or (d) TAM-STAR or TAM-GUARD White Elastomeric Coating at a rate of 2 gals. per 100 sq. ft.

Maintenance of the surface coating is required.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

CAUTION: The National Institute for Occupational Safety and Health (NIOSH) has concluded that fumes of heated asphalt are a potential occupational carcinogen. Apply heat to these products only when required for proper application and only in a well ventilated area. Avoid breathing the fumes, and avoid skin contact. Do not burn these products.