

TAMKO® TW-60

WATERPROOFING MEMBRANE

MANUFACTURED IN COLUMBUS, KS

PRODUCT DATA

DESCRIPTION

Information included in this product data sheet was current at time of printing.

To obtain a copy of the most current version of this product data sheet, visit us online at tamko.com or call us at 800-641-4691.

TAMKO® TW-60 is a self-adhering sheet membrane consisting of a rubberized asphalt adhesive and a polymer film as the top surface.

- Treated release film for ease of installation and handling
- Available in factory pre-cut widths of 6", 9", 12", 18", and 39-3/8" rolls
- Available in Winter and Summer Grade Formulations
- 5-year Limited Warranty and Arbitration Agreement

USES: TW-60 is used for below-grade waterproofing of foundation walls, tunnels, earth shelters, and similar structures. TW-60 is also used for waterproofing plaza decks, parking decks, balconies, and terraces.

WATERPROOFING PRODUCTS BEGIN TO AGE AS SOON AS THEY ARE EXPOSED TO NATURE. BUILDINGS EXPERIENCE AGING FACTORS DIFFERENTLY, SO IT IS DIFFICULT TO PREDICT HOW LONG WATERPROOFING PRODUCTS WILL LAST. THAT'S WHY TAMKO PROVIDES A LIMITED WARRANTY THAT INCLUDES A BINDING ARBITRATION CLAUSE AND OTHER TERMS AND CONDITIONS WHICH ARE INCORPORATED HEREIN BY REFERENCE. YOU MAY OBTAIN A COPY OF THE LIMITED WARRANTY AT TAMKO.COM OR BY CALLING 1-800-641-4691.

LIMITATIONS

- TW-60 must not be left exposed to sunlight for more than 30 days
- Membrane must be applied when air, substrate, and membrane temperatures are above 40°F
- Membrane must not come into contact with products containing coal-tar pitch
- Not intended for use on roofs or prolonged exposure to temperatures above 200°F

PRODUCT DATA

Roll Width [†]	Roll Size [†]	Coverage per Ctn. ^{††}	Rolls per Ctn.
6"	6" × 61'	183'	6
9"	9" × 61'	183'	4
12"	12" × 61'	183'	3
18"	18" × 61'	183'	2
39-3/8"	39-3/8" × 61'	187.45' per roll ^{††}	1
Asphalt Modifier	Styrenic Block Copolymer		
Product Thickness [†]	60 mil		

[†]Subject to manufacturing variation

^{††}When applied according to application instructions

TYPICAL PHYSICAL PROPERTIES

Test	ASTM Standards	Minimum Physical Properties
Tensile, Film	ASTM D 882	>6,300 psi
Puncture Resistance	ASTM E 154	60 lb. (min.)



P.O. Box 1404
Joplin, MO 64802-1404
800-641-4691
tamko.com

WARNING: This product contains crystalline silica and formaldehyde. Crystalline silica and formaldehyde have been classified as "known human carcinogens" by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. This product also contains oxidized asphalt. Occupational exposure to oxidized asphalt and its emissions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as "known" or "probable human carcinogen". The physical nature of this product may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of this product. Take precautions to prevent breathing and contact with skin.